

## **Corrosion and Hydrogen Permeation in H<sub>2</sub>S Environments with O<sub>2</sub> Contamination, Part 2: Impact of H<sub>2</sub>S Partial Pressure**

Martien Duvall Deffo Ayagou, Gaurav Joshi, Thi Tuyet Mai Tran, Eliane Sutter, Bernard Tribollet, Christophe Mendibide, Claude Duret-Thual, Nicolas Ferrando, Jean Kittel

► **To cite this version:**

Martien Duvall Deffo Ayagou, Gaurav Joshi, Thi Tuyet Mai Tran, Eliane Sutter, Bernard Tribollet, et al.. Corrosion and Hydrogen Permeation in H<sub>2</sub>S Environments with O<sub>2</sub> Contamination, Part 2: Impact of H<sub>2</sub>S Partial Pressure. Corrosion, National Association of Corrosion Engineers, 2019, 75 (4), pp.389-397. 10.5006/3092 . hal-02070657

**HAL Id: hal-02070657**

**<https://hal.sorbonne-universite.fr/hal-02070657>**

Submitted on 18 Mar 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Corrosion and hydrogen permeation in H<sub>2</sub>S environments with O<sub>2</sub> contamination – 2: Impact of H<sub>2</sub>S partial pressure

Martien Duvall Deffo Ayagou, \* Gaurav R. Joshi, \*\*  
Thi Tuyet Mai Tran, \*\*\* Eliane Sutter, \*\*\* Bernard  
Tribollet, \*\*\* Christophe Mendibide, \* Claude Duret-  
Thual, \* Nicolas Ferrando, \*\*\*\* Jean Kittel, †, \*\*

## ARTICLE INFO

### Article history:

Received Day Month Year (This style is Article History and Keywords)

Accepted Day Month Year

Available Day Month Year

### Keywords: (This style is Article Info subhead)

- A. Hydrogen sulfide
- B. Hydrogen permeation
- C. Hydrogen induced cracking
- D. Sulfide stress cracking

\* Institut de la Corrosion Site de Saint-Etienne, ZA du parc secteur Gampille, Fraisses, F-42490 (FRANCE)

\*\* IFP Energies Nouvelles, Rond point de l'échangeur de Solaize BP3, Solaize, F-69360 (FRANCE)

\*\*\* Sorbonne Université, CNRS, Laboratoire Interfaces et Systèmes Electrochimiques (LISE), Paris F-75005 (FRANCE)

\*\*\*\* IFP Energies Nouvelles, 1 et 4 avenue de bois préau, Rueil-Malmaison, F-92852 (FRANCE)

† Corresponding author: Email: jean.kittel@ifpen.fr

## ABSTRACT

Materials selection in the oil and gas industry relies on engineering standards, such as NACE TM0177 and NACE TM0284, which stipulate that oxygen pollution should be avoided during materials testing in H<sub>2</sub>S-containing media. In this second paper, as part of a series of articles that evaluate how traces of oxygen modify the corrosion of pure iron and hydrogen permeation across iron membranes in H<sub>2</sub>S-containing solutions, we investigate the impact of changing the H<sub>2</sub>S partial pressure from 100 kPa to 0.1 kPa. It is found that bulk solution chemistry for all H<sub>2</sub>S partial pressures changes with time, due to the formation of H<sub>2</sub>S-O<sub>2</sub> reaction products (sulfates, sulfites and thiosulfates) which results in bulk solution acidification. Electrochemical and weight-loss measurements confirm that Fe corrosion rates in 'control' well-deaerated H<sub>2</sub>S-containing solutions decrease with decreasing H<sub>2</sub>S partial pressure, although these are observed to be much higher under continuous oxygen pollution. With decreasing H<sub>2</sub>S partial pressure, hydrogen uptake in Fe also decreases,

due to lower and lower concentrations of dissolved H<sub>2</sub>S and the associated increase in pH. However, even at 1 and 0.1 kPa H<sub>2</sub>S, permeation efficiencies remain close to 100 % when no O<sub>2</sub> pollution is present. The hydrogen uptake is always relatively lower in Fe exposed to oxygen-polluted H<sub>2</sub>S solutions. Permeation efficiencies decrease continuously. From electrochemical data and surface characterization, we attribute our observations at lower H<sub>2</sub>S partial pressures to the disruptive effect of oxygen on the nature of sulfide corrosion products', and hydrogen entry promotion, along with the contribution of an additional 'non-hydrogenating' cathodic reaction.

## INTRODUCTION

The extent of the degradation of carbon and low-alloy steel components during upstream production varies across a plethora of environmental and operating conditions. Factors such as acid gas concentration, solution chemistry, fluid flow regimes and oil/water cut influence engineering decisions that range from materials selection to inhibitor dosing. Focusing on acid gas concentration, typically expressed in pressures or mol% in the petroleum sector, ferritic materials exposed to environments containing hydrogen sulfide (H<sub>2</sub>S) can suffer hydrogen induced cracking (HIC), sulfide stress cracking (SSC), or stress-oriented hydrogen induced cracking (SOHIC). This is well attributed to the corrosive, and H-entry promoting nature, of dissolved H<sub>2</sub>S.

ISO15156 guides the selection of carbon and low-alloy steels for use in existing or potential sour operating conditions.<sup>1</sup> Often, a pH(y)-P<sub>H<sub>2</sub>S</sub>(x) diagram (see ISO 15156-2) is used as a frame of reference during materials testing; the diagram plots solution acidity (pH) vs. H<sub>2</sub>S partial pressures (kPa) across orders of magnitude and suggests relative 'levels of severity'. Concerning materials qualification, standards such as NACE TM0177 and TM0284 stipulate materials testing criteria. A critical one is the effective deaeration of H<sub>2</sub>S-containing test solutions and maintaining low dissolved concentrations of oxygen during the testing period (typically 30 days).<sup>2,3</sup> Standards mention that, '*O<sub>2</sub> contamination may induce an increase of the corrosion rate and reduce hydrogen evolution and hydrogen entry into the steel*', although '*systematic studies of the parameters affecting these phenomena have not been reported in the literature*'. Ambient oxygen has the potential to pollute a test medium, through incorrect or insufficient deaeration of the initial test solution, a poor sealing of test reactors, the use of plastic tubing permeable to oxygen, and a multitude of operations during the test (e.g. solution sampling, pH adjustment). From an industrial point of view, oxygen ingress into sour systems through compressors or vapor recovery units, is well recognized.<sup>4</sup>

In the first paper of this series, we presented how traces of oxygen exacerbate the corrosion of, but diminish the hydrogen permeation across, iron membranes exposed to 35 g/L NaCl saturated with H<sub>2</sub>S at 24°C and atmospheric pressure (partial pressure of hydrogen sulfide gas = 100 kPa) as a function of time over 3-4 weeks.<sup>5</sup> In this second paper, with the pH-P<sub>H<sub>2</sub>S</sub> diagram of ISO15156 in mind, we extend the study parameters to lower applied P<sub>H<sub>2</sub>S</sub>, i.e. how does the same O<sub>2</sub> pollution influence phenomena in solutions containing lower dissolved H<sub>2</sub>S. As done in the first paper, only model systems are considered here, with pure iron as the test material, the use of unbuffered test solutions, and H<sub>2</sub>S or H<sub>2</sub>S/N<sub>2</sub> mixtures used to control the acid gas concentration (no CO<sub>2</sub>). As before, we follow the evolution of the solution chemistries, and the effect on Fe corrosion and hydrogen uptake, as a function of time. Material surface characterization through X-ray diffraction (XRD) further enables the understanding of phenomena that take place in such media.

## Experimental procedure

The relevant preparation and experimental procedures are detailed in part 1.<sup>5</sup> Pure H<sub>2</sub>S (> 99.5% H<sub>2</sub>S) and H<sub>2</sub>S/N<sub>2</sub> gas cylinders (10 % H<sub>2</sub>S / balance N<sub>2</sub>), (1 % H<sub>2</sub>S / balance N<sub>2</sub>) and (0.1 % H<sub>2</sub>S / balance N<sub>2</sub>) were used to establish the different partial pressures of 10 kPa, 1 kPa and 0.1 kPa respectively in the tests. In order to determine the impact of O<sub>2</sub> contamination, a number of tests were conducted with pure iron exposed to 35 g/L NaCl solution at various H<sub>2</sub>S partial pressure (P<sub>H<sub>2</sub>S</sub>) between 100 kPa and 0.1 kPa. Several types of measurements were carried out: 1) continuous in-situ pH measurement and periodic sampling of test solution for chemical analysis; 2) weight-loss and surface analysis of small coupons; 3) EIS at the H-entry face of the membrane; 4) hydrogen permeation at the H-exit face of the membrane.

## Results and Discussion

### Impact of oxygen on corrosive medium

The evolution of test solution pH with or without oxygen pollution are shown in Figure 1. Note that since the balance gas is nitrogen, the bulk solution pH is higher at lower P<sub>H<sub>2</sub>S</sub>.


**Figure 1: Time evolution of pH of test solutions at various H<sub>2</sub>S partial pressures. Impact of continuous O<sub>2</sub> contamination corresponding to 500 ppb weight (P<sub>O<sub>2</sub></sub> = 1.3 kPa).**

For short exposures times, no difference is measured between the test with O<sub>2</sub> contamination (red symbols) and the reference test without O<sub>2</sub> (black symbols). Initial pH values are determined by acid gas content (i.e. P<sub>H<sub>2</sub>S</sub>) while FeS solubility equilibrium controls the final pH, for the test condition without O<sub>2</sub>. For comparison, saturated pH values calculated with Cormed™ are reported in Table 1, and compared with experimental values at short exposures. Except at the lowest P<sub>H<sub>2</sub>S</sub>, an excellent match is found between experimental and calculated values. As expected, reference tests without O<sub>2</sub> contamination exhibit no significant changes of pH with time, once the saturated value is reached. On the contrary, O<sub>2</sub> contamination systematically induces an acidification of the test solution over time. The rate of pH drop is greatest for the 100 kPa case, and approximately similar for the remaining P<sub>H<sub>2</sub>S</sub> systems, found to lie between 0.15 and 0.3 pH unit per 100 hours exposure. Considering the usual duration of a standard SSC test (720 hours), a pH drop more than 1 pH unit may thus be anticipated under a comparable oxygen ingress.


**Table 1: Comparison between experimental pH at the beginning of the tests and calculated pH at FeS saturation in 35 g/L NaCl solution at 24 °C.**

In order to measure the O<sub>2</sub> – H<sub>2</sub>S reaction chemistry, which is responsible for solution acidification,<sup>5</sup> periodic sampling of the test solution was performed for the experiments at 100 kPa H<sub>2</sub>S and 10 kPa H<sub>2</sub>S. Analysis by ionic chromatography (IC) shows that sulfate (SO<sub>4</sub><sup>2-</sup>) is the main species formed. Its concentration increased linearly with time in presence of O<sub>2</sub> contamination, while it stayed at minute levels in reference conditions without O<sub>2</sub> (Figure 2). According to the literature,

the reaction paths leading to sulfate involves intermediate steps with thiosulfate formation accompanied by the release of H<sup>+</sup>:<sup>6,7</sup>



The more stable sulfate species, and elemental sulfur, may then be formed by various paths, e.g. by direct oxidation:



**Figure 2: Time evolution of sulfate concentration for the tests at 100 kPa and 10 kPa H<sub>2</sub>S in model systems.**

Such results of pH change could be indicative of O<sub>2</sub> contamination during SSC qualification tests. Indeed, NACE TM0177 states that ‘oxygen contamination is evident by a cloudy (opaque) appearance of the test solution when the H<sub>2</sub>S gas enters the test vessel’. As soon as steel is present, darkening of the test solution occurs with iron sulfide precipitation, masking any transparency changes that take place in the early stages. We suggest that *in situ* pH monitoring or chemical detection of sulfates might thus represent more robust methods to detect oxygen contamination in such systems.

### Weight-loss corrosion and surface analysis

The weight-loss corrosion rates of pure iron (average of 2 coupons) exposed to solutions at various P<sub>H<sub>2</sub>S</sub>, with and without O<sub>2</sub> contamination, are compared in Table 2. Four replicates were performed under 100 kPa H<sub>2</sub>S, from which standard deviations were determined. All other tests were carried out only once. This Table also includes corrosion rates obtained from electrochemical measurements at the entry face of the membrane. The increasing discrepancy between weight-loss and electrochemical measurements, with decreasing P<sub>H<sub>2</sub>S</sub>, will be discussed in the electrochemical section of this article.

**Table 2: Impact of O<sub>2</sub> contamination on corrosion rate of pure iron weight-loss coupons exposed to 35 g/L NaCl solution saturated with H<sub>2</sub>S at various partial pressures for 2 to 4 weeks.**

Corrosion rates in reference conditions without O<sub>2</sub> decrease monotonically as P<sub>H<sub>2</sub>S</sub> decreases. The corrosion rate drops from 0.5 mm/year (100 kPa H<sub>2</sub>S) to 0.1 mm/year at 0.1 kPa H<sub>2</sub>S. This decrease of corrosion rate correlates with the measured increase in pH. This is expected, since dissociated H<sup>+</sup><sub>aq</sub> is one of the cathodic reagents.<sup>8</sup> Indeed, the concentration of dissolved H<sub>2</sub>S is expected to decrease from 1x10<sup>-1</sup> M to 1x10<sup>-4</sup> M from 100 kPa to 0.1 kPa, which also, is recognized as a relevant oxidizing agent that contributes to iron corrosion.<sup>9</sup> We expect that the water reduction reaction also becomes a relevant contributing cathodic reaction at the highest pH/lowest P<sub>H<sub>2</sub>S</sub> test solutions.

In the presence of O<sub>2</sub> contamination, a systematic aggravation of corrosion is seen, compared to reference condition without O<sub>2</sub>. At P<sub>H<sub>2</sub>S</sub>

of 100 kPa and 10 kPa, corrosion rates in the presence of oxygen were doubled. Curiously, however, the amplitude of this aggravation increases by more than an order of magnitude ( $> 10x$ ) as  $P_{H_2S}$  decreases even further towards the lowest dissolved  $H_2S$  concentrations and highest pH. To discuss that the measured increase is not a result of 'classical' oxygen cathodic corrosion, we consider the concentrations of the dissolved molarities in bulk solution. For the 100 kPa and 10 kPa systems - the  $[H_2S]_{aq}$  are 0.1 M and 0.01 M respectively (vs.  $2 \times 10^{-5}$  M of  $[O_2]_{aq}$ ), i.e. in massive excess. In 1 kPa and 0.1 kPa -  $H_2S$  concs are  $1 \times 10^{-3}$  and  $1 \times 10^{-4}$  mol. The ratios of  $H_2S(aq):O_2(aq)$ , which remain roughly the same throughout the testing period due to a continuous bubbling of both gases, decrease (from  $5000x \rightarrow 5x$ ); but, corrosion rates increase by an order of magnitude for the two lower  $H_2S$  partial pressures. This peculiarity of massively high corrosion rate is not explicable by  $[O_2]_{aq}$  as a cathodic reactant alone as it is simply not present in high enough concentration to support a high cathodic reduction current (on the order of  $100 \mu A \text{ cm}^{-2}$ ). The bulk solution acidification effect must somewhat contribute, although, again, considering the magnitude of the change in  $[H^+]_{aq}$ , it is insufficient to cause more than a 10-fold increase in corrosion rates at the lowest  $P_{H_2S}$ . Indeed, the base pH is much higher (from pH 5 to 6.5).

In order to understand this curiosity, reference to surface characterization data is helpful. Figure 3 presents typical X-ray diffraction patterns taken from Fe coupon surfaces that were exposed to solutions under high partial pressure (100 kPa) and low partial pressure (1 kPa)  $H_2S$ , with and without oxygen pollution. For the 100 kPa case, sample surfaces comprised exclusively of iron sulfides, in particular mackinawite; under 500 ppb oxygen pollution, we observe additional signatures of mixture of pyrrhotite/pyrite/troilite (it is difficult to distinguish between these since they share many diffraction peaks). At lower  $P_{H_2S}$  of 10 kPa, predominantly mackinawite, with some other iron sulfides, peaks were detected. However, under oxygen pollution, we also can clearly discern the presence of magnetite and elemental sulfur ( $S_8$ ) in addition to the iron sulfides (including greigite). Greigite is an iron sulfide mineral that is considered to form in the presence of traces of oxygen.<sup>10</sup> This is quite significant since the surface products of elemental sulfur and magnetite are never detected at higher partial pressures of  $H_2S$ . Indeed, elemental sulfur corrosion deposits are known to enormously accelerate the corrosion of iron, through galvanic coupling effects.<sup>4</sup> It is expected to be particularly insidious in salty brines and the prior existence of an iron sulfide overlayer,<sup>11</sup> as reported by field experience. It may well explain why the highest weight loss corrosion rates are detected at the lowest  $H_2S$  partial pressures. This experimental finding will be further discussed in the electrochemical section of this article.

**Figure 3: XRD patterns from pure iron surfaces after long term exposure to  $H_2S$ -containing 35 g/L NaCl (24°C), with and without 500 ppb oxygen pollution, at (a)  $P_{H_2S} = 100$  kPa and (b) 1 kPa**

### Electrochemical study

In addition to weight-loss coupons, electrochemical measurements were conducted on the iron membrane. Typical EIS measurements of the entry face of the membrane at various times of exposure are presented in Figure 4. In this Figure, the plots labelled (a, c, e and f) display EIS Nyquist spectra taken from sample surfaces exposed to different  $P_{H_2S}$  solutions without oxygen; whereas the (b, d, f and h) plots show EIS data taken from surfaces exposed to the same, different  $P_{H_2S}$  solutions, albeit with oxygen pollution.

**Figure 4: Typical impedance of pure iron in 35 g/L NaCl solution saturated with  $H_2S$  at 100 kPa (a, b), 10 kPa (c, d), 1 kPa (e, f) and 0.1 kPa (g, h), without (a, c, e, g) and with (b, d, f, h)  $O_2$  pollution.**

Except for the tests conducted at 100 kPa  $H_2S$  without  $O_2$  contamination and at long exposures (Figure 4.a), all other EIS Nyquist curves are deemed to be quite comparable with each other. They present a high frequency capacitive loop, possibly followed by a second semi-circle at low frequency. This low frequency semi-circle is hardly visible at 1 kPa  $H_2S$  and 0.1 kPa  $H_2S$ . We discuss in a previous article that the impedance behavior of pure iron exposed to 100 kPa  $H_2S$  is characterized by a two-step anodic reaction with an adsorbed intermediate.<sup>12</sup> The charge transfer resistance from which corrosion rate could be calculated is represented by the diameter of the high-frequency time constant observed in Nyquist plots. We extend this interpretation to evaluate the charge transfer resistance for all test conditions as a function of time. A more complex model, including a porous film contribution, had to be used to analyze EIS data obtained at 100 kPa  $H_2S$ , as explained in details in previous articles.<sup>5; 12</sup> From the charge transfer resistances determined from the EIS data above, it is then possible to present the evolution of instantaneous corrosion rates, with the application of the Stern and Geary relationship ( $B = 40$  mV/decade used here) and Faraday's law. The results obtained are illustrated on Figure 5.

**Figure 5: Time evolution of corrosion rates of pure iron determined from EIS analysis.**

As expected, without  $O_2$  pollution, corrosion rates decrease sharply in short exposure periods, and then stabilize for the remaining duration of the experiment. The time window of the initial drop of corrosion rate is comparable to pH changes, suggesting that kinetics of corrosion are driven by test solution acidity and  $FeS$  formation/solution saturation.

With  $O_2$  pollution, the corrosion rates starts to decrease at short exposure times, similarly to the case without  $O_2$ . However, rather than stabilizing, they then increases sharply as pH decreases. Looking closely at the profile of the EIS corrosion rates, it is interesting to note that the corrosion rate does not simply increase steadily from the early stages of exposure, but undergoes a sharp transition that imposes a faster rate of corrosion rate. The trend signifies sudden and enormously increasing rate of reaction, that we assign to be intimately related to modifications to the protectivity of the sulfide corrosion product films and the deposition of elemental sulfur, as determined by XRD. Field experience suggests that steel corrosion in the presence of elemental sulfur, iron sulfides and dissolved chlorides can proceed at enormous rates and lead to rapid failure of equipment through deposit galvanic corrosion.<sup>4</sup> Furthermore, reference to the geothermal power industry research's efforts on the deliberate oxidation of  $H_2S$  (to eliminate it) through injecting oxygen, is highly relevant here.<sup>13</sup> The reactions of dissolved hydrogen sulfide and oxygen to form thiosulfates, sulfates and elemental sulfur are suspected to be 'autocatalytic', with the possible involvement of co-catalyst radical polysulfido-ions that likely need to build up in concentration.<sup>13</sup> The  $H_2S$ - $O_2$  reactions can be catalysed at active transition metal surfaces (e.g. Ni, Co, Fe), and potentially at iron oxides and iron sulfides. One reproducible experimental feature observed at all  $P_{H_2S}$  to support the 'autocatalytic oxidation of  $H_2S$  leading to  $S_8$  deposition' hypothesis is a steady rising

corrosion rate followed by a very sudden rise at a given moment during immersion. An induction period prior to an unusually high reaction rate is characteristic of an autocatalytic reaction.<sup>4;13</sup>

As noted in Table 2, a significant deviation between weight-loss corrosion rates and electrochemical values is observed at lower  $P_{H_2S}$ , with the former vastly exceeding the latter. The difference is certainly exacerbated in the case of  $O_2$  pollution, reaching a factor of x20. Upon reflection, we believe that the highest corrosion rates of weight-loss coupons, compared to the entry face of permeation membranes, relates to the different fluid flows that they experience in the experiment cell over the duration of the test (see Fig 2 in Deffo Ayagou *et al.*<sup>12</sup>). Weight-loss coupons were typically suspended just above the purging gas frit. As a consequence, we expect that these samples were subjected a quite unpredictable, turbulent flow if compared against the permeation membrane; the latter is situated at the end of a tube (diameter = 40 mm, length = 60 mm) that connects to the main body of the cell. We conclude that the permeation membrane largely experiences a laminar, low flow. Considering the distance between the gas frit and the permeation membrane (>100 mm), it is quite likely that only the solution reaction  $O_2$ - $H_2S$  products (thiosulfates and sulfates), rather than dissolved oxygen, interact with the permeation membrane surface. In contrast, the weight-loss coupons were subjected to a direct gas exposure during the first seconds of gas injection. We suspect this permits the direct oxidation of  $H_2S$  with dissolved oxygen on these catalytic corrosion coupon surfaces, which explains the presence of elemental sulfur at the surface of the coupons for the tests at 1 and 0.1 kPa  $H_2S$ . In these tests, dissolved  $H_2S$  concentration is sufficiently weak to allow unreacted aqueous and gaseous  $O_2$  to reach the coupon surfaces and oxidizing sulfides to elemental sulfur/oxidise aqueous  $H_2S$ . As a consequence, the electrochemical measurements that we report in this paper must be considered representative of test solutions containing  $O_2$  -  $H_2S$  reaction products, rather than a vigorous exposure of oxygen gas to the metal surface. Conversely, a relatively good correlation between both methods of corrosion rate evaluation is generally observed at the higher  $P_{H_2S}$  of 100 kPa and 10 kPa. We consider this to be an effect of the vast excess of  $[H_2S]_{aq}$  with respect to  $[O_2]_{aq}$ , where the low dissolved oxygen concentration is quickly diminished upon reaction with  $H_2S$  to form thiosulfates and sulfates. The corrosion of iron in the relatively higher  $P_{H_2S}$  media appears to be governed by the pH (3.5-5) and dissolved concentration of  $H_2S$  on cathodic reactions, rather than flow effects.<sup>14</sup>

The evolution of open circuit potential values of the pure iron electrode in different partial pressure  $H_2S$  media is presented in Figure 6, (a) without and (b) with oxygen pollution. Visually, it is clear to see that under oxygen pollution these values increase considerably more if compared against deaerated conditions. Table 3 lists the change in open circuit potential between the beginning and after two to four weeks of sample exposure. Since the corrosion rate and open circuit potential are both increasing, mixed potential theory would suggest that it is the increasing cathodic reaction kinetics would play the important role in corrosion acceleration. The open circuit potential rise in the oxygen polluted conditions also correlates with the increasing solution acidity (Figure 1). We suspect that the increase in cathodic corrosion reaction kinetics might arise from increasing  $H^+$  concentration as well as from reaction (2) (thiosulfate reduction). Indeed, the role of elemental sulfur cannot be ruled out.

**Figure 6: Time evolution of open circuit potentials of pure iron exposed to 35 g/L NaCl solution saturated with  $H_2S$  at various partial**

**pressures for 2 to 4 weeks, (a) without oxygen and (b) with oxygen pollution.**

**Table 3: Impact of  $O_2$  contamination on open circuit potential value change (from start), of pure iron exposed to 35 g/L NaCl solution saturated with  $H_2S$  at various partial pressures for 2 to 4 weeks.**

Figure 7 (a – h) presents the results of the hydrogen permeation tests at different partial pressures of  $H_2S$ , with and without oxygen gas pollution of the solutions. Since EIS measurements were carried out simultaneously with hydrogen permeation, it is possible to compare the evolution of corrosion current density and hydrogen permeation current density as a function of time through evaluating the hydrogen permeation efficiency ( $E_{perm}$ ), defined as the ratio between permeation current and corrosion current. The validity of its usage in such experiments is outlined in Paper 1.

**Figure 7: Comparisons between  $J_{corr}$  and  $J_{perm}$ , and evolution of the permeation efficiency, as a function of time. Tests at 100 kPa (a, b), 10 kPa (c, d), 1 kPa (e, f) and 0.1 kPa (g, h), without (a, c, e, g) and with (b, d, f, h)  $O_2$  pollution.**

For the studied conditions, it is observed that average permeation currents diminish with decreasing  $P_{H_2S}$  (i.e. lower  $[H_2S]_{aq}$  and  $[H^+]_{aq}$ ). Quite remarkably, and as already observed in the previous article, permeation efficiencies are close to 100 % for all tests without  $O_2$  pollution, albeit more scattering appears at 0.1 kPa  $H_2S$ . For this test condition (0.1 kPa  $H_2S$  without  $O_2$ ), we believe that corrosion current densities were overestimated, due to insufficient influence of the charge transfer resistance in the frequency range of impedance measurements (Figure 4.g). In such conditions, permeation current density might be a more reliable indication of corrosion current density than EIS analysis. Such results with no  $O_2$  pollution illustrate the strong power of  $H_2S$  in hydrogen entry promotion, with 100 % efficiency for as low as 0.1 kPa  $H_2S$ . This behavior is observed in very specific hydrogen permeation systems, provided that the entire corrosion current contributes to hydrogen entry (i.e. negligible film protection, hydrogen entry promoters), that there is no impediment to hydrogen entry (i.e. no filming or competitive adsorption), that no hydrogen diffusion limitation in the bulk of the metal occurs (i.e. thin membrane, low trapping) and that the hydrogen extraction is efficient (i.e. Pd coated).<sup>15; 16</sup>

Conversely, under oxygen pollution, the hydrogen permeation current is always found to be weaker relative to the reference solutions. Our previous article discusses the continuous decrease of the hydrogen permeation current for the  $O_2$ -polluted 100 kPa system. Interestingly, this is no longer the case for lower  $P_{H_2S}$  solutions. Rather, a lower permeation current (hydrogen diffusion) is simply maintained throughout the experiment duration. Since the hydrogen extraction setup is always identical, and identical membranes are used, this is almost certainly a limitation on hydrogen uptake in the oxygen-polluted systems. The impact of  $O_2$  pollution is better illustrated by  $E_{perm}$ . Considering this parameter, similar trends are observed whatever the  $P_{H_2S}$  considered in the study. At short immersion times, when  $O_2$  -  $H_2S$  reactions have not yet had time to modify the system, high permeation efficiencies are obtained, typically between 60 % and

100 %. Then, as  $O_2 - H_2S$  reaction products modify the test solution and the surface scales, a continuous decrease of the permeation efficiency is seen. This decrease is mainly due to the increase of corrosion rate, which takes place at nearly constant  $J_{perm}$ , suggesting the participation of an additional 'non-hydrogenating' cathodic reaction that drives corrosion. We expect this contribution comes from thiosulfate reduction (reaction 2) and the subsequent corrosion acceleration effects of elemental sulfur.

## Conclusions

The effect of traces of oxygen on the corrosion of, and hydrogen permeation across, pure iron was studied in a 35 g/L NaCl test solution saturated with  $H_2S$  partial pressures ranging from 100 kPa to 0.1 kPa, as a function of time over 2 to 4 weeks.  $O_2$  pollution was introduced in a continuous manner in the test gas, at a partial pressure of 1.3 kPa corresponding to 500 mass ppb dissolved  $O_2$  at equilibrium. The following conclusions were drawn from this study:

- ❖ With  $H_2S$  partial pressure from 100 kPa to 0.1 kPa, and in the resulting pH range of 4 to 6,  $O_2$  pollution modifies the test solution chemistry by forming thiosulfates, and the stable sulfate species. These reactions appear to induce a test solution acidification, that should extend to over 1 pH unit over 720 hours.
- ❖  $O_2$  pollution significantly enhances the corrosion of iron in all cases, compared to reference solution without  $O_2$ . At low  $PH_2S$ , as the iron surface is placed close to the source of  $O_2$  entry, the  $H_2S-O_2$  oxidation reactions take place at the metal/metal sulfide surface, depositing elemental sulfur, and accelerating corrosion rates by an order of magnitude (20x) in the process. When the metal surface is sufficiently far to be exposed only to  $H_2S - O_2$  reaction products, the factor drops to approximately 2x on average for the time scale of our experiments.
- ❖ Without  $O_2$  pollution, mackinawite is generally the principal iron sulfide species detected. With  $O_2$  pollution at high  $PH_2S$ , surfaces are revealed to consist of additional iron sulfide (pyrrhotite, troilite) signatures; at lower  $PH_2S$ , clear diffraction peaks for greigite, magnetite and elemental sulfur are discerned.
- ❖ Without  $O_2$  pollution, hydrogen permeation density is found to be in the same range as the corrosion current density, irrespective of the  $PH_2S$ , implying a 100 % permeation efficiency. This is a clear illustration of the strong hydrogen entry promotion by  $H_2S$ .
- ❖ Conversely, with  $O_2$  pollution, hydrogen permeation efficiency drops from 60 – 100 % initially, to as low as 5 % after 2 to 4 weeks. This drop is mainly due to the continuous increase of corrosion rate, indicating that  $H_2S - O_2$  reactions promote the onset and participation of additional non hydrogenating cathodic corrosion reactions.

In the third part of this series of papers, similar experiments will be carried out in experimental conditions more representative of industrial applications. Pure iron membrane will be replaced by low alloy steel, and tests will be conducted in acetate buffered solutions.

## Acknowledgements

The authors express their gratitude to Alexandre Bonneau for his active participation in the implementation of the experimental setup and Remy Mingant, for EIS analysis. The contribution of IFPEN analysis department in the surface characterization and solution analysis is also greatly acknowledged.

## References

1. ISO 15156-2:2015, "Petroleum and Natural gas industries - Materials for use in  $H_2S$ -containing environments in oil and gas production - Part 2: Cracking resistant carbon and low alloy steels, and the use of cast iron," (International Organization for Standardization, 2015).
2. NACE TM0284-2016, "Evaluation of pipeline and pressure vessel steels for resistance to hydrogen-induced cracking"(Houston, TX: NACE International, 2016).
3. NACE TM0177-2016, "Laboratory testing of metals for resistance to sulfide stress cracking and stress corrosion cracking in  $H_2S$  environments" (Houston, TX: NACE International, 2016).
4. J. Boivin, S. Oliphant, "Sulfur corrosion due to oxygen ingress," Corrosion 2011, held 13-17 March, paper 120 (Houston, TX: NACE International, 2011).
5. M.D. Deffo Ayagou, J. Kittel, C. Mendibide, C. Duret Thual, k. belkhadiri, T.T. Mai Tran, E. Sutter, B. Tribollet, N. Ferrando, Corrosion 74, 11 (2018): p. 1192–1202.
6. J.L. Crolet, M. Pourbaix, A. Pourbaix, "The Role of trace amounts of oxygen on the corrosivity of  $H_2S$  media," in Corrosion/91, ed. NACE International, 10-15 March, Corrosion/91, paper 22 (1991).
7. Y. Song, A. Palencsár, G. Svenningsen, J. Kvarekvål, T. Hemmingsen., Corrosion 68, NACE (2012): p. 662–671.
8. Y. Zheng, B. Brown, S. Nestic, Corrosion 70 (2013): p. 351-365.
9. J. Kittel, F. Ropital, F. Grosjean, E.M.M. Sutter, B. Tribollet, Corrosion Science 66 (2013): p. 324–329.
10. X. Wen, P. Bai, B. Luo, S. Zheng, C. Chen, Corrosion Science 139 (2018): p. 124–140.
11. G. Mike, J. Slofstra, W. Sudds, E, D.T. Thill, "Corrosion experiences and inhibition practices managing wet sour salty gas pipeline environments contaminated with sulfur deposits", Corrosion 2003, held 16-20 March, paper 174 (Houston, TX: NACE International, 2003).
12. M.D. Deffo Ayagou, T.T. Mai Tran, B. Tribollet, J. Kittel, E. Sutter, N. Ferrando, C. Mendibide, C. Duret-Thual, Electrochimica Acta 282 (2018): p. 775–783.
13. O. Weres, L. Tsao, "Reaction of hydrogen sulfide with oxygen in the presence of sulfite: Prepared at the Earth Sciences Division at Lawrence Berkeley Laboratory, University of California," LBL-11377, 1983.
14. S.Wach, A.P.Miodownik, J.Mackowiak, Corrosion Science 6 (1966): p. 271–285.
15. T. Zakroczymski, Z.Szklarska-Smiatowska, M.Smiatowski, Werkstoffe und Korrosion 27 (1976): p. 625-630.

## TABLE CAPTIONS

Table 1: Comparison between experimental pH at the beginning of the tests and calculated pH at FeS saturation in 35 g/L NaCl solution at 24 °C.

Table 2: Impact of  $O_2$  contamination on corrosion rate of pure iron weight-loss coupons exposed to 35 g/L NaCl solution saturated with  $H_2S$  at various partial pressures for 2 to 4 weeks.

Table 3: Impact of  $O_2$  contamination on open circuit potential value change (from start), of pure iron exposed to 35 g/L NaCl solution saturated with  $H_2S$  at various partial pressures for 2 to 4 weeks.

## FIGURE CAPTIONS

1 Figure 1: Time evolution of pH of test solutions at various H<sub>2</sub>S partial  
2 pressures. Impact of continuous O<sub>2</sub> contamination corresponding to  
3 500 ppb weight (P<sub>O<sub>2</sub></sub> = 1.3 kPa).

4 Figure 1: Time evolution of pH of test solutions at various H<sub>2</sub>S partial  
5 pressures. Impact of continuous O<sub>2</sub> contamination corresponding to  
6 500 ppb weight (P<sub>O<sub>2</sub></sub> = 1.3 kPa).Figure 2: Time evolution of sulfate  
7 concentration for the tests at 100 kPa and 10 kPa H<sub>2</sub>S in model  
8 systems.

9 Figure 3: XRD patterns from pure iron surfaces after long term  
10 exposure to H<sub>2</sub>S-containing 35 g/L NaCl (24°C), with and without 500  
11 ppb oxygen pollution, at (a) P<sub>H<sub>2</sub>S</sub> = 100 kPa and (b) 1 kPa

12 Figure 4: Typical impedance of pure iron in 35 g/L NaCl solution  
13 saturated with H<sub>2</sub>S at 100 kPa (a, b), 10 kPa (c, d), 1 kPa (e, f) and 0.1  
14 kPa (g, h), without (a, c, e, g) and with (b, d, f, h) O<sub>2</sub> pollution.

15 Figure 5: Time evolution of corrosion rates of pure iron determined  
16 from EIS analysis.Figure 5: Time evolution of corrosion rates of pure  
17 iron determined from EIS analysis.

18 Figure 6: Time evolution of open circuit potentials of pure iron exposed  
19 to 35 g/L NaCl solution saturated with H<sub>2</sub>S at various partial pressures  
20 for 2 to 4 weeks, (a) without oxygen and (b) with oxygen pollution.

21 Figure 7: Comparisons between J<sub>corr</sub> and J<sub>perm</sub>, and evolution of the  
22 permeation efficiency, as a function of time. Tests at 100 kPa (a, b), 10  
23 kPa (c, d), 1 kPa (e, f) and 0.1 kPa (g, h), without (a, c, e, g) and with (b,  
24 d, f, h) O<sub>2</sub> pollution.

For Review Only

25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60

- 1
- 2
- 3
- 4
- 5
- 6
- 7
- 8
- 9
- 10
- 11
- 12
- 13
- 14
- 15
- 16
- 17
- 18
- 19
- 20
- 21
- 22
- 23
- 24
- 25
- 26
- 27
- 28
- 29
- 30
- 31
- 32
- 33
- 34
- 35
- 36
- 37
- 38
- 39
- 40
- 41
- 42
- 43
- 44
- 45
- 46
- 47
- 48
- 49
- 50
- 51
- 52
- 53
- 54
- 55
- 56
- 57
- 58
- 59
- 60

For Review Only






Figure 1 a




Figure 1 b




Figure 1 c




Figure 1 d




Figure 2




Figure 3 a




Figure 3 b





Figure 4 a b







Figure 4 c d





Figure 4 e f





Figure 4 g h




Figure 5 a




Figure 5 b




Figure 5 c




Figure 5 d




Figure 6 a






Figure 6 b




Figure 7 a




Figure 7 b




Figure 7 c




Figure 7 d




Figure 7 e




Figure 7 f




Figure 7 g






Figure 7 h

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60

**Table 1: Comparison between experimental pH at the beginning of the tests and calculated pH at FeS saturation in 35 g/L NaCl solution at 24 °C.**

PH <sub>2</sub> S (kPa)	100	10	1	0.1
Exp. pH at 24 hours without O <sub>2</sub>	4.3	5.0	5.7	6.8
Exp. pH at 24 hours with O <sub>2</sub>	4.2	5.0	5.5	6.7
Calculated pH at FeS saturation	4.3	5.0	5.6	6.3

For Review Only

**Table 1: Impact of O<sub>2</sub> contamination on corrosion rate (in  $\mu\text{m}/\text{year}$ ) of pure iron weight-loss coupons exposed to 35 g/L NaCl solution saturated with H<sub>2</sub>S at various partial pressures for 2 to 4 weeks.**

P <sub>H2S</sub>	Without O <sub>2</sub>		With O <sub>2</sub>	
	Weight-loss	EIS	Weight-loss	EIS
100 kPa	489 +/- 68	490	976 +/- 248	900
10 kPa	284	230	523	330
1 kPa	163	53	2257	96
0.1 kPa	101	4	1111	44

For Review Only

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60

**Table 1: Impact of O<sub>2</sub> contamination on open circuit potential value change (from start), of pure iron exposed to 35 g/L NaCl solution saturated with H<sub>2</sub>S at various partial pressures for 2 to 4 weeks.**

P <sub>H2S</sub>	100 kPa	10 kPa	1 kPa	0.1 kPa
H <sub>2</sub> S	+11 mV	+17 mV	+21 mV	+9 mV
H <sub>2</sub> S + O <sub>2</sub>	+40 mV	+85 mV	+49 mV	+43 mV

For Review Only