



**HAL**  
open science

# 2D MoO<sub>3</sub>-xS<sub>x</sub>/MoS<sub>2</sub> van der Waals Assembly: a Tunable Heterojunction with Attractive Properties for Photocatalysis

Masoud Shahrokhi, Pascal Raybaud, Tangui Le Bahers

► **To cite this version:**

Masoud Shahrokhi, Pascal Raybaud, Tangui Le Bahers. 2D MoO<sub>3</sub>-xS<sub>x</sub>/MoS<sub>2</sub> van der Waals Assembly: a Tunable Heterojunction with Attractive Properties for Photocatalysis. ACS Applied Materials & Interfaces, 2021, 13 (30), pp.36465-36474. 10.1021/acsami.1c08200 . hal-03353918

**HAL Id: hal-03353918**

**<https://ifp.hal.science/hal-03353918v1>**

Submitted on 24 Sep 2021

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

**2D MoO<sub>3-x</sub>S<sub>x</sub>/MoS<sub>2</sub> van der Waals Assembly: a Tunable Heterojunction  
with Attractive Properties for Photocatalysis**

Masoud Shahrokhi <sup>1</sup>, Pascal Raybaud <sup>1,2\*</sup> and Tangui Le Bahers <sup>1\*</sup>

<sup>1</sup>*Univ Lyon, ENS de Lyon, CNRS, Université Claude Bernard Lyon 1, Laboratoire de Chimie*

*UMR 5182, F-69342 Lyon, France*

<sup>2</sup>*IFP Energies nouvelles, Rond-point de l'échangeur de Solaize, BP 3, 69360 Solaize, France*

Authors for correspondence: pascal.raybaud@ifpen.fr; tangui.le\_bahers@ens-lyon.fr

## **ABSTRACT**

2D van der Waals (vdW) heterostructures currently attract much attention in widespread research fields where semiconductors materials are key. With the aim of gaining insights into photocatalytic materials, we use density functional theory (DFT) calculations within HSE06 functional to analyze the evolution of opto-electronic properties and high frequency dielectric constant profiles of various 2D  $\text{MoO}_{3-x}\text{S}_x/\text{MoS}_2$  heterostructures modified by chemical and physical approaches. While the  $\text{MoO}_3/\text{MoS}_2$  heterostructure is a type III heterojunction associated to a metallic character, we find that exchanging with sulfur the terminal-oxo atoms of the  $\text{MoO}_{3-x}\text{S}_x$  single layer (SL) enables to shift its CB position above the VB position of the  $\text{MoS}_2$  SL. This trend gives rise to a type II heterojunction where the band gap and charge transfer within the two layers are driven continuously by the S-concentration in  $\text{MoO}_{3-x}\text{S}_x$  SL. This fine tuning leads to a versatile type II heterostructure proposed to provide a direct Z-scheme system valuable for photocatalytic water splitting.

## **KEYWORDS**


$\text{MoS}_2$ ,  $\text{MoO}_3$ , heterojunction, Z-scheme, DFT, photocatalysis, water splitting

## INTRODUCTION

Two-dimensional (2D) semiconductors heterostructures are widely investigated to design specific electronic devices such as tunneling transistors and light-emitting diodes.<sup>1-3</sup> Another recent exploration of such semiconductors is prompted by the growing interest of photocatalytic materials where the electronic structure of the heterojunction must be tuned to optimize light absorption and separation of the photogenerated charge carriers.<sup>4</sup> Heterojunctions are classified into three types, namely, straddling (type I), staggered (type II), and broken-gap (type III).<sup>5,6</sup> In type I heterojunction and under light irradiation (Figure 1), the electrons and holes accumulate at the conduction band (CB) and the valence band (VB) of SC II, respectively. In type III heterojunction, the CB and the VB levels of SC I have higher potentials than VB of the SC II which breaks the gap. For the type II heterojunction, the CB and VB levels of SC I have higher potentials than the corresponding levels of the SC II. Therefore, thermodynamically, the photogenerated electrons may transfer from SC II to SC I, while the photogenerated holes migrate from SC I to SC II, resulting in a spatial separation of electron-hole pairs. Nevertheless, depending on the relative CB SC I and VB SC II positions and kinetic effects, the photogenerated electrons in SC I may preferentially recombine with the holes from SC II than the transfer of an electron from SC II to SC I. This alternative transfer mode corresponds to a Z-scheme working principle of type II heterojunction,<sup>7,8</sup> where electrons and holes are not only spatially separated but also have a large reductive and oxidative potentials (respectively) making this configuration close to photosynthesis which is appealing for photocatalysis.<sup>7,9,10</sup>

Moreover within such Z-scheme heterojunctions, the maximum photoconversion efficiency in a water-splitting process is theoretically much higher (25%) compared to single semiconductor (12%).<sup>11</sup> This advantage of Z-scheme heterojunction is unfortunately compensated by the

challenges of material synthesis, and of tuning the charge transfer following either a standard type II or a true Z-scheme.<sup>9</sup> One possible way to address these challenges is to explore heterostructures made of the assembly of two-dimensional (2D) layered materials<sup>12</sup> forming stacked 2D/2D layered structures, which electronic properties are weakly affected by the formation of the heterostructure due to the van der Waals (vdW) interaction between layers.



**Figure 1.** Schematic illustration of the band alignments and charge transfer mechanisms for three different types of heterojunctions formed by coupling of two semiconductors.

Among various 2D nanomaterials, whose graphene is the most well-known representative, 2D transition metal oxides (TMO) and transition metal dichalcogenides (TMD) are actively investigated.<sup>13-17</sup> In particular,  $\alpha$ -MoO<sub>3</sub> (*Pnma* space group) is an n-type semiconductor with a wide experimental band gap of ~3.2 eV,<sup>18,19</sup> while 2H-MoS<sub>2</sub> (*P63/mmc* space group) exhibits an indirect band gap of ~1.23 eV.<sup>20,21</sup> Although recent experimental<sup>15,22-26</sup> and theoretical works<sup>25,27,28</sup> highlight the possible synthesis and key interests of MoO<sub>3</sub>/MoS<sub>2</sub> heterostructures for various applications, it remains unknown to which extent the optoelectronic properties of such 2D heterostructure can be optimized to match the requirements of photocatalytic materials. DFT with hybrid functional study demonstrated that the MoO<sub>3</sub>/MoS<sub>2</sub> heterostructure is a type III

heterojunction, being a good candidate for a tunnel field effect (TFET)-type device<sup>25,28</sup> but not for photocatalytic materials. However, we recently showed by DFT calculations that the optoelectronic properties of  $\alpha$ -MoO<sub>3-x</sub>S<sub>x</sub> (S-doped  $\alpha$ -MoO<sub>3</sub>) and 2H-MoS<sub>2-x</sub>O<sub>x</sub> (O-doped 2H-MoS<sub>2</sub>) bulk materials can be tuned by anionic isovalent-atom doping (S and O respectively),<sup>20</sup> which opens opportunities to further explore 2D heterostructures made of  $\alpha$ -MoO<sub>3-x</sub>S<sub>x</sub>/2H-MoS<sub>2-x</sub>O<sub>x</sub> layers. Hence, the objective of the present work is to explore by DFT (HSE06 functional) how a fine chemical and physical change of the 2D MoO<sub>3</sub>/MoS<sub>2</sub> heterostructure can switch the heterojunction from type III to type II heterojunction with adjustable band gaps, relative CB/VB positions, charge transfers and dielectric functions. These new heterostructures are very promising materials for photocatalysis and more generally for semiconductor-based devices.

## METHODS

The geometry optimizations of all heterostructures was investigated by means of DFT calculations with periodic boundary condition with the PBE functional<sup>29</sup> as implemented in Vienna ab initio simulation package (VASP)<sup>30,31</sup> and a  $3 \times 3 \times 1$  k-point grid. The van der Waals contributions were described by using the semi-empirical Grimme D3 approach<sup>32</sup>. We represented these 2D structures by a periodic array of layers separated by a vacuum region in excess of 20 Å to avoid interactions between periodic images. Electronic wave functions have been expanded using a plane wave basis set with a cutoff energy of 500 eV for the valence electrons. The interaction between the valence and the core electrons for Mo, O and S atoms was described with the projected augmented wave (PAW) method.<sup>33</sup> The convergence criterion for the SCF was set up at  $10^{-5}$  eV/atom. All geometry optimization have been done using the conjugate-gradient method<sup>34</sup> until none of the residual Hellmann–Feynman forces exceeded  $10^{-3}$  eV/Å. Since ordinary DFT within the PBE/GGA

underestimate the band gap, all the electronic properties were computed via single-point calculations by using the range separated hybrid Heyd–Scuseria–Ernzerhof (HSE06) exchange correlation functional<sup>35</sup> on the PBE optimized geometries with a  $6 \times 6 \times 1$  k-point mesh using ab initio CRYSTAL17 code.<sup>36</sup> This code works within periodic boundary conditions and adopts localized Gaussian-type function basis sets (BSs) allowing a fast evaluation the Hartree-Fock exchange. The following BSs were used: Mo\_SC\_HAYWSC-311(d31)G\_cora\_1997<sup>37</sup> (for Mo atoms), S\_86-311G\*\_lichanot\_1993<sup>38</sup> (for S atoms) and O\_8-411d11G\_valenzano\_2006<sup>39</sup> (for O atoms). To calculate the high frequency dielectric function, the electronic density with ( $\rho(z)|_{\vec{E}_{ext}}$ ) and without ( $\rho(z)|_0$ ) external electric field was calculated using CRYSTAL package and averaged in the plane parallel to the  $z$ -axis. It is then smoothed using a nanoscale averaging<sup>33</sup> along the out-of-plane direction. A more detailed presentation of the procedure is given in SI. The optical properties were calculated through the frequency dependent dielectric matrix  $\epsilon_{\alpha\beta}(\omega)$  within HSE06 functional by using VASP based on a sum overstate approach. The number of empty conduction bands was converged for each structure with respect to standard calculations. The absorption coefficient can be evaluated from dielectric matrix using the Kramers-Kronig transformation:<sup>40</sup>

$$\alpha_{\alpha\beta}(\omega) = \frac{2\omega k_{\alpha\beta}(\omega)}{c} = \frac{\omega \text{Im}(\epsilon_{\alpha\beta}(\omega))}{c n_{\alpha\beta}(\omega)} \quad (1)$$

where  $c$  is the speed of light in vacuum.  $n_{\alpha\beta}$  and  $k_{\alpha\beta}$  are real and imaginary parts of the complex refractive index, and are known as the refractive index and the extinction index, respectively. More details on methods can be found in Supporting Information.

In term of functional, the dielectric-dependent density functional (whose the fraction of Hartree Fock-exchange is inversely proportional to the infinite dielectric constant)<sup>41-43</sup> could be an interesting alternative to the HSE06 functional. However, the difficulty to define the dielectric

constant of a 2D-material and the one of a heterojunction makes the use of such functionals not straightforward. A not-system dependent functional such as HSE06 seems more appropriate for 2D-heterojunction (as illustrated in this work).

## RESULTS AND DISCUSSION


**Pristine 2D MoO<sub>3</sub>/MoS<sub>2</sub> heterostructure.** The MoO<sub>3</sub>/MoS<sub>2</sub> system was simulated through a (3 × 3) MoO<sub>3</sub> monolayer supercell with pre-optimized lattice parameters ( $a = 11.12 \text{ \AA}$  and  $b = 11.73 \text{ \AA}$ ) chosen as a substrate of a (4 × 4) MoS<sub>2</sub> monolayer placed on top of it (Figure 2a). The mismatch of MoS<sub>2</sub> lattice parameters is less than 2% in comparison with the individual layer which ensures a low strain. After optimizing the atomic positions of the heterostructure using DFT-PBE-D3<sup>29,32</sup> functional (see Methods), the equilibrium distance between the O<sub>t</sub>-plane of MoO<sub>3</sub> and S-plane of MoS<sub>2</sub>,  $d_{(S-O_t)}$  in the MoO<sub>3</sub>/MoS<sub>2</sub> heterostructure, is found at 2.86 Å, with an exothermic interlayer binding energy of -0.7 eV.

The band structures and the partial density of states (PDOS) determined with HSE06 functional<sup>35,44</sup> (Figure 2d) show that the MoO<sub>3</sub>/MoS<sub>2</sub> interface is a type III heterojunction resulting from the lower CB position of single-layer (SL) MoO<sub>3</sub> (-6.56 eV) than the VB position of SL MoS<sub>2</sub> (-6.36 eV) (Figure 2c), in agreement with the previous theoretical results of Gao et al.<sup>28</sup> A charge transfer occurs from MoS<sub>2</sub> to MoO<sub>3</sub> within the junction (Figure 2b and S3). The differential Bader charge<sup>45</sup> evaluated between the heterojunction and individual layers, reveals a +0.5 charge on MoS<sub>2</sub> layer (-0.5 charge on MoO<sub>3</sub> layer) in the heterostructure. This charge transfer between the layers point to a strong donor–acceptor interaction in MoO<sub>3</sub>/MoS<sub>2</sub> composite structure. Since, there is no accumulation of electrons in the interlayer region, the MoO<sub>3</sub> and MoS<sub>2</sub> layers are coupled both by vdW and electrostatic forces.



To overcome the type III heterojunction, CB and VB positions of each distinct MoS<sub>2</sub> and MoO<sub>3</sub> single-layer must be displaced. We first explored a physical approach by increasing the number of layers for each individual component (Supporting Information S2.2 and Figure S2). However, the HSE06 band structure of MoO<sub>3</sub> is relatively insensitive to the number of layers: the band gap varying from 2.83 eV for a monolayer to 2.96 eV for the bulk material. Moreover, the VB and CB edges of MoO<sub>3</sub> nanosheets remain almost unchanged from one monolayer to 5 monolayers. In contrast, the fundamental band gap of MoS<sub>2</sub> layers increases monotonically when the number of layers decreases in good agreement with STM/STS experiments:<sup>46</sup> for single, double and triple layers MoS<sub>2</sub>, the calculated bandgaps were 2.38 eV, 1.96 eV and 1.87 eV respectively, while they were measured at 2.40 eV, 2.10 and 1.75 eV respectively (Table S2). It is important to note here that the appropriate bandgap to compare here is the fundamental bandgap and not the optical one (as discussed in the following reference [11]).


More specifically, in MoS<sub>2</sub> nanosheets the CB edge positions remain almost constant while VB edge position shifts to higher energies by increasing the number of layers (Figure S1 and Figure S2). As a consequence, any stacking of MoO<sub>3</sub> and MoS<sub>2</sub> multilayers will not change the type of heterojunction since the relative positions of the MoS<sub>2</sub> multilayers VB and MoO<sub>3</sub> multilayers CB are not inverted, whatever the number of layers considered.



**Figure 2.** Optimized structure (a), planar-averaged charge density difference  $\langle \Delta\rho(z) \rangle$ : electron accumulation in cyan and electron depletion in green (b), conduction and valence band-edge positions respect to vacuum level (c) and band structure and PDOS for each layers (d) for pristine  $\text{MoO}_3/\text{MoS}_2$  heterojunction. The lower edge of the conduction band (orange colour) and upper edge of the valence band (blue colour) are presented along with the band gap in electron volts. The dashed black lines in (c) indicate the water stability limits for hydrogen and oxygen evolution and the dashed pink lines in (c) and (d) indicate the Fermi energy. The absolute potential of the standard hydrogen electrode was taken as 4.44 eV at a pH = 0.

The second approach, more chemical, was inspired by our recent work on doped bulk  $\text{MoO}_3$  and  $\text{MoS}_2$  materials,<sup>20</sup> and consists in substituting oxygen (sulfur respectively) atoms by sulfur (oxygen respectively) atoms in  $\text{MoO}_3$  ( $\text{MoS}_2$  respectively) single-layer leading to  $\text{MoS}_x\text{O}_{3-x}$  ( $\text{MoO}_x\text{S}_{2-x}$ ) single-layer. The detailed structures, energetic stability and optoelectronic properties of these


systems are reported in the Supporting Information S4. Substituting oxygen atoms (terminal oxo-species preferentially, Figure S4) with sulfur atoms in MoO<sub>3</sub> SL decreases the band gap with values ranging from 2.5 eV to 2.0 eV (Figure 3) while keeping the indirect character of the band gap (Figure S8). This is mainly due to the formation of states located either on S atoms in the band gap or at the top of the VB. The analysis of absolute band edge position indicates that the VB and CB positions of individual SL MoO<sub>3</sub> continuously move to higher energies by increasing S concentration (Figure 3). On the other hand, substituting S atoms with O atoms in MoS<sub>2</sub> SL does not affect neither the band gap nor the CB/VB positions, except for very high concentrations (Figure S9 and S12). In summary, heterostructures combining MoO<sub>3</sub> SL where oxygen is substituted by sulfur atoms with MoS<sub>2</sub> multilayer is the most promising one because it allows a fine tuning of band positions. Assuming first that the bands of each materials will not be affected by the formation of a van der Waals 2D heterojunction, Figure 3 shows that a 2D heterostructure combining a MoS<sub>2</sub> SL with MoO<sub>3</sub> SL doped should enable to switch from a type III to a type II heterojunction by varying the content of S in the MoO<sub>3-x</sub>S<sub>x</sub> SL. In the case of a type II heterojunction, the CB/VB positions seems compatible with water splitting photocatalytic application. It is also important to note that the cell parameters of the S-doped MoO<sub>3</sub> SL are almost not affected by the doping (see Table S3) because only the substitution O<sub>t</sub> planes atoms are considered. In other words, the mismatch between S-doped MoO<sub>3</sub> and MoS<sub>2</sub> supercells used to simulate the heterojunction remains low (~2%). The goal of subsequent sections is to investigate whether these proposals based on individual systems remain valid once the heterostructure is explicitly built.



**Figure 3.** Calculated conduction and valence band-edge positions for S-substituted SL MoO<sub>3</sub> and 1L-6L MoS<sub>2</sub> with respect to vacuum level and standard hydrogen electrode. The lower edge of the conduction band (orange colour) and upper edge of the valence band (blue colour) are presented along with the band gap in electron volts. The dashed black lines indicate the water stability limits for hydrogen and oxygen evolution. The absolute potential of the standard hydrogen electrode was taken as 4.44 eV at a pH = 0.

**Type II 2D MoO<sub>3</sub>/MoS<sub>2</sub> heterostructure.** Figure S13 illustrates the various configurations of MoS<sub>x</sub>O<sub>3-x</sub>/MoS<sub>2</sub> bilayer heterostructures with different concentrations of S atoms replacing the terminal oxo-species of MoO<sub>3</sub>. The interlayer distance between MoO<sub>3</sub> and MoS<sub>2</sub> layers is enhanced by increasing the sulfur concentration (Table S5) while interface binding energy becomes more exothermic revealing the enhanced stability of these heterostructures. For low S concentrations into MoO<sub>3</sub> layer (up to 3.75%), the metallic character of the initial MoO<sub>3</sub>/MoS<sub>2</sub> heterostructure is maintained while for S concentration equal or greater than 5.6%, a metal-semiconductor transition occurs (Figure S14 and Table S5). As expected from Figure 3 and Figure S14, VB of these materials is located on Mo *4d* states of MoS<sub>2</sub> and the conduction band on the Mo *4d* states of MoO<sub>3</sub> with an indirect band gap. Note that the band gap can only be opened when the doping sulfur atoms are located in the interlayer region. Interestingly, Figure 4 reveals that the

band gap is continuously enlarged by increasing S concentration into MoO<sub>3</sub> layer from 0.15 eV for  $x_S=5.6\%$  to 1.05 eV for  $x_S=33\%$  (as suspected from the individual component behaviors, Figure 3). Reversely, the Bader charge transfer decreases with increasing S concentration. For the largest S concentration, it is almost negligible. However, for intermediate S concentration such as 9.3%, this charge transfer is about +0.17 e.




**Figure 4.** Evolution of the bandgap and the Bader charge transfer of the heterostructure S-doped MoO<sub>3</sub>/MoS<sub>2</sub> as a function of the sulfur concentration in MoO<sub>3</sub> layer.

In what follows, we focus on this interesting case of S-doped MoO<sub>3</sub>/MoS<sub>2</sub> interface for  $x_S=9.3\%$  (corresponding to MoS<sub>0.28</sub>O<sub>2.72</sub> SL) which exhibits type II character but with a small bandgap (around 0.4 eV). Figure 5 illustrates the optimized structure and electronic properties. The CB position of MoO<sub>3</sub> has higher energy than VB of MoS<sub>2</sub>, the Bader charge transfer from MoS<sub>2</sub> to MoS<sub>0.28</sub>O<sub>2.72</sub> is decreased (0.17 e<sup>-</sup>) with respect to the pristine MoS<sub>2</sub>/MoO<sub>3</sub> system (0.5 e<sup>-</sup>). This is consistent with the charge density difference plots (Figure 5b and S15), which show electron accumulation in the interlayer region of S-doped MoO<sub>3</sub>/MoS<sub>2</sub> indicating a weak covalent bond between the two layers. The PDOS of Figure 5d, shows that the VB and CB of the S-doped MoO<sub>3</sub>/MoS<sub>2</sub> interface are delocalized in MoS<sub>2</sub> and MoS<sub>0.28</sub>O<sub>2.72</sub> layers respectively, confirming the

formation of the well-defined type II band alignment which facilitates the separation of photo-induced carriers.

The working principle of a type II heterojunction can be “standard”, corresponding to the thermodynamic motion of the charge carriers, or a Z-scheme, meaning that kinetically electron and holes will recombine at the interface between the two semiconductors (Figure 1). Tuning properly the bandgap of the type II  $\text{MoS}_x\text{O}_{3-x}/\text{MoS}_2$  heterojunction as a function of S-concentration is probably key to govern the working principle. A large bandgap with a negligible charge transfer (for  $x_S \geq 15\%$ ) favoring the “standard” working principle while a small bandgap (for  $x_S \approx 9-10\%$ ) orienting toward a Z-scheme one. In this latter case, the electron transfer between  $\text{MoS}_2$  and  $\text{MoS}_x\text{O}_{3-x}$ , even reduced, is non-negligible which may favor the recombination of electrons and holes at the interface, pushing a little bit more toward a Z-scheme working principle of this heterostructure for photocatalysis. In the case of water splitting, the CB/VB positions of the two semi-conductors with respect to  $\text{H}^+/\text{H}$  and  $\text{H}_2\text{O}/\text{O}_2$  potentials imply that  $\text{MoS}_2$  may reduce the proton while  $\text{MoS}_{0.28}\text{O}_{2.72}$  will oxidize water (Figure 5).



**Figure 5.** Optimized structure (a), planar-averaged charge density difference  $\langle \Delta\rho(z) \rangle$  (electron accumulation in cyan and electron depletion in green) (b), conduction and valence band-edge positions respect to vacuum level (c) and band structure and PDOS for each layers (d), for S-doped  $\text{MoS}_{0.28}\text{O}_{2.72}/\text{MoS}_2$  heterojunction ( $x_S = 9.3\%$ ). The lower edge of the conduction band (orange colour) and upper edge of the valence band (blue colour) are presented along with the band gap in electron volts. The dashed black lines in (c) indicate the water stability limits for hydrogen and oxygen evolution. The absolute potential of the standard hydrogen electrode was taken as 4.44 eV at a pH = 0.


As shown in Supporting Information S4.2, we propose that the S-content of the  $\text{MoS}_x\text{O}_{3-x}$  layer can be reached experimentally by the chemical potential of sulfur imposed by the partial pressure of well-chosen sulfiding agent (such as  $\text{H}_2\text{S}$  or else). It has been reported that Mo-oxysulfide can be synthesized experimentally by sulfiding  $\text{MoO}_3$  crystalline compounds or nano-particles dispersed on a support through an O/S exchange process. For instance, the sulfidation of crystalline

MoO<sub>3</sub> by H<sub>2</sub>S was characterized by IR and XPS techniques which revealed the possible formation of MoOS<sub>2</sub> intermediate.<sup>47</sup> EXAFS experiments revealed the formation of small MoO<sub>x</sub>S<sub>y</sub> entities from Mo-oxide supported on alumina under H<sub>2</sub>/H<sub>2</sub>S treatment.<sup>48</sup> Moreover molecular (NH<sub>4</sub>)<sub>2</sub>MoO<sub>2</sub>S<sub>2</sub> compounds are known to exist.<sup>49</sup> If so, the transitions from type III to type II heterojunction and within type II from a Z-scheme to a standard working principle could be determined by tuning the given partial pressure of such a sulfiding agent at the preparation step of the material. In photocatalytic reaction conditions, no H<sub>2</sub>S is formed which will not modify the properties of the heterojunction. Moreover, the impact of water either as a reactant or as a solvent on the CB/VB positions of the heterojunction should remain minor, since the Mo sites present at the interface exhibit a complete coordination sphere as found in the bulk. So, we suspect that water will mainly interact physically with the heterostructure, while chemical interactions of water will occur on a small number of Mo defect sites located at edges of the 2D-layers of MoO<sub>3</sub> and MoS<sub>2</sub>. This interaction of water with the heterostructure should have a minor impact on the optoelectronic properties determined here.

**Dielectric profiles of the heterojunctions.** While decisive, band positions are not the only important properties of a material for its use as a photocatalyst: the electron-hole separation is also key. To analyze the exciton dissociation, we applied a procedure detailed in Supporting Information 1.3 to evaluate the high frequency dielectric profiles of these new heterostructures.<sup>50-</sup><sup>54</sup> It is worth to note in our current work, we employed for the first time, hybrid functional of HSE06<sup>35</sup> to provide accurate estimations. The high frequency dielectric profiles  $\epsilon_{\infty}(z)$  for individual SL MoO<sub>3</sub>, individual SL MoS<sub>2</sub> and S-doped MoO<sub>3</sub>/MoS<sub>2</sub> heterojunctions are depicted in Figure 6: a relevant case (MoO<sub>2</sub>S) of doping is reported which correspond to the former type II



heterojunctions. Doping S into MoO<sub>3</sub> layer in these heterojunctions obviously enhances the peaks height of dielectric profile of MoO<sub>3</sub> layer but also slightly increases the peaks height of dielectric profile of MoS<sub>2</sub> layer because of the increase of polarity induced by sulfur. As a consequence, the effective dielectric constants,  $\epsilon_{\text{eff}}$ , of the S-doped MoO<sub>3</sub> heterojunctions is greater (4.49) than the one of MoO<sub>3</sub> (2.85). Moreover, the effective dielectric constant of the S-doped MoO<sub>3</sub>/MoS<sub>2</sub> interface is also slightly larger (4.52) than the sum of the individual SL MoO<sub>3</sub> and SL MoS<sub>2</sub> (4.33) when considered as non-interacting probably because of the covalent interaction between the two layers increasing the polarizability of the interface.



**Figure 6.** The high frequency dielectric constant profile along out-of-plane for SL MoO<sub>3</sub>, MoSO<sub>2</sub>, MoS<sub>2</sub> and MoSO<sub>2</sub>/MoS<sub>2</sub> hetero-structures. The effective dielectric constant for each structure is also reported in the caption.


The optical analysis for S-doped MoO<sub>3</sub>/MoS<sub>2</sub> heterojunctions (Figure S17) indicates highly anisotropic optical properties for all 2D systems along in-plane and out-of-plane. The absorption coefficient of S-doped MoO<sub>3</sub>/MoS<sub>2</sub> heterojunctions is higher than SL MoO<sub>3</sub> in the UV-vis window and it enhances by increasing S concentration in the structures. In general, despite the indirect band gap nature of these heterojunctions, high absorption coefficients were attained ( $\sim 10^5 \text{ cm}^{-1}$ ) that is

higher than the typical absorption coefficient value for direct band gap semiconductors across the entire UV-vis range<sup>20</sup>. These two complementary properties confirm the high potential interest of S-doped MoO<sub>3</sub>/MoS<sub>2</sub> heterojunctions.

**Sensitivity to the number of layers involved in the heterostructure.** In order to optimize at best the composite material, we also investigate the impact of varying the number of MoS<sub>2</sub> and MoO<sub>2</sub>S layers in the heterostructures. Although we have already shown that the number of layers was not impacting the individual component of the heterostructure, it remains key to determine how the MoS<sub>2</sub>/MoO<sub>2</sub>S heterojunction itself depends on the number of layers. This analysis could provide practical insights into the further design of the materials regarding its sensitivity to layers' stacking during the synthesis step.

Thus, we explore the impact of increasing the MoS<sub>2</sub> and MoO<sub>3</sub> layers on the optoelectronic properties and as well as the VB and CB band positions of their formed interface. We first consider the case of two MoS<sub>2</sub> layers (2L) in the S-doped MoO<sub>3</sub> (x<sub>S</sub>=33%)/MoS<sub>2</sub> heterostructure. The interlayer binding energy for S-doped MoO<sub>3</sub>/2L-MoS<sub>2</sub> interface is -1.2 eV indicating a stabilizing effect for this composite by increasing the number of layers. Figure 7a and b illustrates the optimized structure and the VB and CB band positions of S-doped MoO<sub>3</sub>/2L-MoS<sub>2</sub> heterostructure. This heterostructure shows a band gap of 1.02 eV allowing us to conclude that the increasing the number of MoS<sub>2</sub> layer has a weak effect on S-doped MoO<sub>3</sub>/MoS<sub>2</sub> heterostructure in terms of band gap. Regarding to their CB and VB band positions, this interface forms a type II heterostructure. Figure S19 shows that the electrons are accumulated in the interlayer regions of S-doped MoO<sub>3</sub>/MoS<sub>2</sub> and of MoS<sub>2</sub>/MoS<sub>2</sub> indicating the weak covalent bond between these layers. The Bader charge analysis indicates that a weak electron transfer (0.025 e<sup>-</sup>) from MoS<sub>2</sub> layer at middle

to MoSO<sub>2</sub> layer while the topmost MoS<sub>2</sub> layer keeps its charge unchanged. From this point of view, the increase of the number of layers does not impact tremendously the heterojunction. Figure S20 presents the dielectric constant profile for S-doped MoO<sub>3</sub>/2L-MoS<sub>2</sub> heterostructure. Our results show that the peaks of dielectric profile in MoSO<sub>2</sub>/2L-MoS<sub>2</sub> interface are significantly enhanced. The reason for this increase is the interaction between S atoms at the nearest layers.



**Figure 7.** Optimized structure and conduction and valence band-edge positions respect to vacuum level for S-doped MoO<sub>3</sub>/2L-MoS<sub>2</sub> (a)-(b) and 3L-S-doped-MoO<sub>3</sub>/MoS<sub>2</sub> (c)-(d) heterostructures. The lower edge of the conduction band (orange colour) and upper edge of the valence band (blue colour) are presented along with the band gap in electron volts. The dashed black lines indicate the water stability limits for hydrogen and oxygen evolution. The absolute potential of the standard hydrogen electrode was taken as 4.44 eV at a pH = 0.

In a second step, we now consider a heterostructure with 3 MoO<sub>3</sub> layers. As discussed before, increasing the number of pristine MoO<sub>3</sub> layers does not produce any change in the VB and CB positions on this material alone. Nevertheless, doping S into MoO<sub>3</sub> can shift the VB and CB positions depending on sulfur concentration. Hence, two different systems of S-doped 3L-MoO<sub>3</sub>/MoS<sub>2</sub> interface with low and high sulfur concentrations were studied: (i) 3L-MoS<sub>0.17</sub>O<sub>2.83</sub>/MoS<sub>2</sub> where only the top layer (interfacial) of O-atoms are substituted by S and (ii) 3L-MoSO<sub>2</sub>/MoS<sub>2</sub>. Figure S21 shows that 3L-MoS<sub>0.17</sub>O<sub>2.83</sub>/MoS<sub>2</sub> has almost a metallic character (bandgap computed around 0.02 eV), although this metallic character is less pronounced than in the former MoO<sub>3</sub>/MoS<sub>2</sub> case. The 3L-MoSO<sub>2</sub>/MoS<sub>2</sub> is a type II heterostructure with a band gap of 0.9 eV (Figure 7c and d) with a similar feature as 1L-S-doped-MoO<sub>3</sub>/MoS<sub>2</sub>. Since the band gap is decreased by 0.1 eV with respect to the 1L-S-doped-MoO<sub>3</sub>/MoS<sub>2</sub> we suspect that this is probably a more favorable configuration for building a Z-scheme system. Furthermore, the effective dielectric function was estimated to be 5.65 and 5.40 for MoSO<sub>2</sub>/2L-MoS<sub>2</sub> and 3L-MoSO<sub>2</sub>/MoS<sub>2</sub> interfaces which are greater than that for 1L-MoSO<sub>2</sub>/MoS<sub>2</sub> system (4.52).

To go beyond the type II-band alignment, it is important to mention that the proposed heterostructure is also a good candidate for photocatalytic applications since it may potentially generate a direct Z-scheme system. Within such as a Z-scheme, the photogenerated electron in the CB of S-doped-MoO<sub>3</sub> will recombine to the photogenerated hole in the VB of MoS<sub>2</sub> leading to very reductant electrons in MoS<sub>2</sub> and oxidant holes in S-doped MoO<sub>3</sub>. This 2 photons process can potentially lead to efficient photoelectrochemical reaction, including water splitting. It is beyond the scope of the present work to determine if such a Z-scheme may preferentially occur to the type-II heterojunction, because this depends on numerous intricate complex effects such as the internal

electric field, band bending, and dynamics of charge carrier. However, we think that this heterostructure deserves to be investigated since it appears that its bandgap, probably one of the main parameters orienting toward type-II or Z-scheme working principle, can be tuned by adapting the number of layers of MoS<sub>2</sub> and the S-doping level in MoO<sub>3</sub>.

## CONCLUSIONS

Through DFT calculations, we proposed strategies to tune the transitions from type III to type II band alignment of materials made of 2D MoO<sub>3-x</sub>S<sub>x</sub>/MoS<sub>2</sub> heterostructure. We found that the optoelectronic properties, absolute valence and conduction band edge positions and high frequency dielectric constant profile of individual 2D MoO<sub>3</sub> and MoS<sub>2</sub> components can be effectively modulated by S-substitution of terminal-oxo species inside the MoO<sub>3-x</sub>S<sub>x</sub> structure. This class of material may thus exhibit a large number of applications depending on the targeted type of heterojunction obtained at low/medium/high S-doping.

At zero or low S-doping ( $\leq 5\%$ ), the heterostructure exhibits a type III heterojunction, while for high S-doping ( $\geq 15\%$ ), the band gap may encompass 1 eV. Interesting, at medium and high S-doping ( $> 5\%$ ), the band-gap and charge transfer of the MoS<sub>2</sub>/MoO<sub>3-x</sub>S<sub>x</sub> heterostructure evolves continuously with the S-concentration in the MoO<sub>3-x</sub>S<sub>x</sub>. In particular, at medium S-doping (9-10%), we identified a 2D MoS<sub>0.28</sub>O<sub>2.72</sub>/MoS<sub>2</sub> heterostructure as a potential photocatalytic material since it may potentially generate a direct Z-scheme system due to the proximity of the CB of S-doped-MoO<sub>3</sub> to the VB of MoS<sub>2</sub> (band gap  $\sim 0.4$  eV). Within such as a Z-scheme, the photogenerated electron in the CB of S-doped-MoO<sub>3</sub> will recombine to the photogenerated hole in the VB of MoS<sub>2</sub> leading to reducing electrons in MoS<sub>2</sub> and oxidant holes in S-doped MoO<sub>3</sub>. We also show that our finding can be extended to heterojunctions with variable numbers of layers

MoS<sub>2</sub> and MoO<sub>3-x</sub>S<sub>x</sub> which certainly offers more versatility to the experimental synthesis of these nano-materials. Moreover, according to our thermodynamic analysis, such MoS<sub>x</sub>O<sub>3-x</sub> structures should be accessible experimentally by well-defined sulfiding agents and conditions which will allow the selective S-substitution of terminal-oxo species present in the MoO<sub>3</sub> layer.

One perspective of the present work could be to determine for which S-doping such a Z-scheme may occur preferentially to the type II heterojunction, by considering intricate effects such as the internal electric field, band bending, and kinetics of charge carriers. Hopefully, this work will open new route for exploring semiconductors made of 2D-heterojunctions with flexible type III/type II transition.

## **ASSOCIATED CONTENT**

### **Supporting Information**

The supporting information contains the details of the thermodynamic analysis; the details of absolute valence and conduction band edge positions; the details of the optoelectronic properties; the details of high frequency dielectric constant of O-doped 2D MoS<sub>2</sub> and S-doped 2D MoO<sub>3</sub> nanosheets. It also contains the structural and electronic properties of S-doped MoO<sub>3</sub>/MoS<sub>2</sub> interface with different S concentration and configuration; the dielectric constant profile for S-doped MoO<sub>3</sub>/2L-MoS<sub>2</sub>, and S-doped 3L-MoSO<sub>2</sub>/MoS<sub>2</sub> interfaces. The details of the methodology and computational setup alongside with the method to obtain the microscopic dielectric constant profile for 2D materials is also presented in supporting information. Finally, the most relevant structures, in POSCAR format, are also reported in Supporting Information

## AUTHOR INFORMATION

### Corresponding Authors

\*E-mail: tangui.le\_bahers@ens-lyon.fr

ORCID: Tangui Le Bahers: 0000-0003-2166-081X

\*E-mail: pascal.raybaud@ifpen.fr

ORCID: Pascal Raybaud: 0000-0003-4506-5062

## ACKNOWLEDGMENTS

This work is part of the “RatiOnAl Design for CATalysis” (ROAD4CAT) industrial chair, project IDEXLYON funded by the French National Research Agency (ANR-16-IDEX-0005) and the Commissariat-General for Investment (CGI) within the framework of Investissements d’Avenir program (“Investment for the future”). The authors thank the SYSPROD project and AXELERA Pôle de Compétitivité for financial support (PSMN Data Center). This work was granted access to the HPC resources of CINES, IDRIS and TGCC under the allocation 2018-080609 made by GENCI.

## References

- (1) Wang, X.; Xia, F.: Stacked 2d Materials Shed Light. *Nat. Mater.* **2015**, *14*, 264-265.
- (2) Withers, F.; Del Pozo-Zamudio, O.; Mishchenko, A.; Rooney, A. P.; Gholinia, A.; Watanabe, K.; Taniguchi, T.; Haigh, S. J.; Geim, A. K.; Tartakovskii, A. I.; Novoselov, K. S.:

Light-Emitting Diodes by Band-Structure Engineering in Van Der Waals Heterostructures. *Nat. Mater.* **2015**, *14*, 301-306.

(3) Novoselov, K. S.; Mishchenko, A.; Carvalho, A.; Neto, A. H. C.: 2d Materials and Van Der Waals Heterostructures. *Science* **2016**, *353*, 6298.

(4) Kou, J.; Lu, C.; Wang, J.; Chen, Y.; Xu, Z.; Varma, R. S.: Selectivity Enhancement in Heterogeneous Photocatalytic Transformations. *Chem. Rev.* **2017**, *117*, 1445-1514.

(5) Özçelik, V. O.; Azadani, J. G.; Yang, C.; Koester, S. J.; Low, T.: Band Alignment of Two-Dimensional Semiconductors for Designing Heterostructures with Momentum Space Matching. *Phys. Rev. B* **2016**, *94*, 035125.

(6) Lei, C.; Ma, Y.; Xu, X.; Zhang, T.; Huang, B.; Dai, Y.: Broken-Gap Type-Iii Band Alignment in WTe<sub>2</sub>/HfS<sub>2</sub> Van Der Waals Heterostructure. *J. Phys. Chem. C* **2019**, *123*, 23089-23095.

(7) Wang, Y.; Suzuki, H.; Xie, J.; Tomita, O.; Martin, D. J.; Higashi, M.; Kong, D.; Abe, R.; Tang, J.: Mimicking Natural Photosynthesis: Solar to Renewable H<sub>2</sub> Fuel Synthesis by Z-Scheme Water Splitting Systems. *Chem. Rev.* **2018**, *118*, 5201-5241.

(8) Maeda, K.: Z-Scheme Water Splitting Using Two Different Semiconductor Photocatalysts. *ACS Catal.* **2013**, *3*, 1486-1503.

(9) Xu, Q.; Zhang, L.; Yu, J.; Wageh, S.; Al-Ghamdi, A. A.; Jaroniec, M.: Direct Z-Scheme Photocatalysts: Principles, Synthesis, and Applications. *Mater. Today* **2018**, *21*, 1042-1063.

(10) Xia, X.; Song, M.; Wang, H.; Zhang, X.; Sui, N.; Zhang, Q.; Colvin, V. L.; Yu, W. W.: Latest Progress in Constructing Solid-State Z Scheme Photocatalysts for Water Splitting. *Nanoscale* **2019**, *11*, 11071-11082.

(11) Le Bahers, T.; Takanabe, K.: Combined Theoretical and Experimental Characterizations of Semiconductors for Photoelectrocatalytic Applications. *J. Photochem. Photobiol. C: Photochem. Rev.* **2019**, *40*, 212-233.

(12) Su, J.; Li, G.-D.; Li, X.-H.; Chen, J.-S.: 2d/2d Heterojunctions for Catalysis. *Adv. Sci.* **2019**, *6*, 1801702.

(13) Yang, T.; Song, T. T.; Callsen, M.; Zhou, J.; Chai, J. W.; Feng, Y. P.; Wang, S. J.; Yang, M.: Atomically Thin 2d Transition Metal Oxides: Structural Reconstruction, Interaction with Substrates, and Potential Applications. *Adv. Mater. Interfaces* **2019**, *6*, 1801160.



- (14) Mak, K. F.; Lee, C.; Hone, J.; Shan, J.; Heinz, T. F.: Atomically Thin MoS<sub>2</sub>: A New Direct-Gap Semiconductor. *Phys. Rev. Lett.* **2010**, *105*, 136805.
- (15) Kumar, R.; Goel, N.; Mishra, M.; Gupta, G.; Fanetti, M.; Valant, M.; Kumar, M.: Growth of MoS<sub>2</sub>-MoO<sub>3</sub> Hybrid Microflowers Via Controlled Vapor Transport Process for Efficient Gas Sensing at Room Temperature. *Adv. Mater. Interfaces* **2018**, *5*, 1800071.
- (16) Sun, J.; Li, X.; Guo, W.; Zhao, M.; Fan, X.; Dong, Y.; Xu, C.; Deng, J.; Fu, Y.: Synthesis Methods of Two-Dimensional MoS<sub>2</sub>: A Brief Review. *Crystals* **2017**, *7*, 198.
- (17) Cai, L.; McClellan, C. J.; Koh, A. L.; Li, H.; Yalon, E.; Pop, E.; Zheng, X.: Rapid Flame Synthesis of Atomically Thin MoO<sub>3</sub> Down to Monolayer Thickness for Effective Hole Doping of WSe<sub>2</sub>. *Nano Lett.* **2017**, *17*, 3854-3861.
- (18) Carcia, P. F.; McCarron, E. M.: Synthesis and Properties of Thin Film Polymorphs of Molybdenum Trioxide. *Thin Solid Films* **1987**, *155*, 53-63.
- (19) Chu, C.-W.; Li, S.-H.; Chen, C.-W.; Shrotriya, V.; Yang, Y.: High-Performance Organic Thin-Film Transistors with Metal Oxide/Metal Bilayer Electrode. *Appl. Phys. Lett.* **2005**, *87*, 193508.
- (20) Shahrokhi, M.; Raybaud, P.; Bahers, T. L.: On the Understanding of the Optoelectronic Properties of S-Doped MoO<sub>3</sub> and O-Doped MoS<sub>2</sub> Bulk Systems: A DFT Perspective. *J. Mater. Chem. C* **2020**, *8*, 9064-9074.
- (21) Kam, K. K.; Parkinson, B. A.: Detailed Photocurrent Spectroscopy of the Semiconducting Group VIB Transition Metal Dichalcogenides. *J. Phys. Chem.* **1982**, *86*, 463-467.
- (22) Yoon, A.; Kim, J. H.; Yoon, J.; Lee, Y.; Lee, Z.: Van Der Waals Epitaxial Formation of Atomic Layered α-MoO<sub>3</sub> on MoS<sub>2</sub> by Oxidation. *ACS Appl. Mater. Interfaces* **2020**, *12*, 22029-22036.
- (23) Yin, Z.; Zhang, X.; Cai, Y.; Chen, J.; Wong, J. I.; Tay, Y.-Y.; Chai, J.; Wu, J.; Zeng, Z.; Zheng, B.; Yang, H. Y.; Zhang, H.: Preparation of MoS<sub>2</sub>-MoO<sub>3</sub> Hybrid Nanomaterials for Light-Emitting Diodes. *Angew. Chem. Int. Ed.* **2014**, *53*, 12560-12565.
- (24) Chen, Z.; Cummins, D.; Reinecke, B. N.; Clark, E.; Sunkara, M. K.; Jaramillo, T. F.: Core-Shell MoO<sub>3</sub>-MoS<sub>2</sub> Nanowires for Hydrogen Evolution: A Functional Design for Electrocatalytic Materials. *Nano Lett.* **2011**, *11*, 4168-4175.

- (25) C, S. K.; Longo, R. C.; Addou, R.; Wallace, R. M.; Cho, K.: Electronic Properties of MoS<sub>2</sub>/MoO<sub>x</sub> Interfaces: Implications in Tunnel Field Effect Transistors and Hole Contacts. *Sci. Rep.* **2016**, *6*, 33562.
- (26) Tessarek, C.; Gridenco, O.; Wiesing, M.; Müssener, J.; Figge, S.; Sebald, K.; Gutowski, J.; Eickhoff, M.: Controlled Laser-Thinning of MoS<sub>2</sub> Nanolayers and Transformation to Amorphous MoO<sub>x</sub> for 2d Monolayer Fabrication. *ACS Applied Nano Mater.* **2020**, *3*, 7490-7498.
- (27) Li, H.; Yu, K.; Tang, Z.; Fu, H.; Zhu, Z.: High Photocatalytic Performance of a Type-II A-MoO<sub>3</sub>@MoS<sub>2</sub> Heterojunction: From Theory to Experiment. *Phys. Chem. Chem. Phys.* **2016**, *18*, 14074-14085.
- (28) Gao, Z.; Zhou, Z.; Tománek, D.: Degenerately Doped Transition Metal Dichalcogenides as Ohmic Homojunction Contacts to Transition Metal Dichalcogenide Semiconductors. *ACS Nano* **2019**, *13*, 5103-5111.
- (29) Perdew, J. P.; Burke, K.; Ernzerhof, M.: Generalized Gradient Approximation Made Simple. *Phys. Rev. Lett.* **1996**, *77*, 3865-3868.
- (30) Kresse, G.; Furthmüller, J.: Efficient Iterative Schemes for Ab Initio Total-Energy Calculations Using a Plane-Wave Basis Set. *Phys. Rev. B* **1996**, *54*, 11169-11186.
- (31) Kresse, G.; Furthmüller, J.: Efficiency of Ab-Initio Total Energy Calculations for Metals and Semiconductors Using a Plane-Wave Basis Set. *Comput. Mater. Sci.* **1996**, *6*, 15-50.
- (32) Grimme, S.; Antony, J.; Ehrlich, S.; Krieg, H.: A Consistent and Accurate Ab Initio Parametrization of Density Functional Dispersion Correction (Dft-D) for the 94 Elements H-Pu. *J. Chem. Phys.* **2010**, *132*, 154104.
- (33) Blöchl, P. E.: Projector Augmented-Wave Method. *Phys. Rev. B* **1994**, *50*, 17953-17979.
- (34) Hestenes, M. R.; Stiefel, E.: Methods of Conjugate Gradients for Solving Linear Systems. *J. Res. Natl. Bureau Standards* **1952**, *49*, 409-436.
- (35) Krukau, A. V.; Vydrov, O. A.; Izmaylov, A. F.; Scuseria, G. E.: Influence of the Exchange Screening Parameter on the Performance of Screened Hybrid Functionals. *J. Chem. Phys.* **2006**, *125*, 224106.

- (36) Dovesi, R.; Erba, A.; Orlando, R.; Zicovich-Wilson, C. M.; Civalieri, B.; Maschio, L.; Rérat, M.; Casassa, S.; Baima, J.; Salustro, S.; Kirtman, B.: Quantum-Mechanical Condensed Matter Simulations with Crystal. *WIREs Comput. Mol. Sci.* **2018**, *8*, e1360.
- (37) Corà, F.; Patel, A.; Harrison, N. M.; Roetti, C.; Richard A. Catlow, C.: Ab Initio Hartree–Fock Study of  $\alpha$ -MoO<sub>3</sub>. *J. Mater. Chem.* **1997**, *7*, 959-967.
- (38) Lichanot, A.; Aprà, E.; Dovesi, R.: Quantum Mechanical Hartree-Fock Study of the Elastic Properties of Li<sub>2</sub>S and Na<sub>2</sub>S. *Physica Status Solidi (b)* **1993**, *177*, 157-163.
- (39) Valenzano, L.; Torres, F. J.; Doll, K.; Pascale, F.; Zicovich-Wilson, C. M.; Dovesi, R.: Ab Initio Study of the Vibrational Spectrum and Related Properties of Crystalline Compounds; the Case of CaCO<sub>3</sub> Calcite. *Z. Phys. Chem.* **2006**, *220*, 893-912.
- (40) Wooten, F.: *Optical Properties of Solids*; Academic Press, 2013.
- (41) Conesa, J. C.: Band Structures and Nitrogen Doping Effects in Zinc Titanate Photocatalysts. *Catal. Today* **2013**, *208*, 11-18.
- (42) Das, T.; Di Liberto, G.; Tosoni, S.; Pacchioni, G.: Band Gap of 3d Metal Oxides and Quasi-2d Materials from Hybrid Density Functional Theory: Are Dielectric-Dependent Functionals Superior? *J. Chem. Theory Comput.* **2019**, *15*, 6294-6312.
- (43) Brawand, N. P.; Vörös, M.; Govoni, M.; Galli, G.: Generalization of Dielectric-Dependent Hybrid Functionals to Finite Systems. *Phys. Rev. X* **2016**, *6*, 041002.
- (44) Heyd, J.; Scuseria, G. E.; Ernzerhof, M.: Hybrid Functionals Based on a Screened Coulomb Potential. *J. Chem. Phys.* **2003**, *118*, 8207-8215.
- (45) Henkelman, G.; Arnaldsson, A.; Jónsson, H.: A Fast and Robust Algorithm for Bader Decomposition of Charge Density. *Comput. Mater. Sci.* **2006**, *36*, 354-360.
- (46) Huang, Y. L.; Chen, Y.; Zhang, W.; Quek, S. Y.; Chen, C.-H.; Li, L.-J.; Hsu, W.-T.; Chang, W.-H.; Zheng, Y. J.; Chen, W.; Wee, A. T. S.: Bandgap Tunability at Single-Layer Molybdenum Disulphide Grain Boundaries. *Nat. Commun.* **2015**, *6*, 6298.
- (47) Weber, T.; Muijsers, J. C.; van Wolput, J. H. M. C.; Verhagen, C. P. J.; Niemantsverdriet, J. W.: Basic Reaction Steps in the Sulfidation of Crystalline MoO<sub>3</sub> to MoS<sub>2</sub>, as Studied by X-Ray Photoelectron and Infrared Emission Spectroscopy. *J. Phys. Chem.* **1996**, *100*, 14144-14150.

(48) Rochet, A.; Baubet, B.; Moizan, V.; Devers, E.; Hugon, A.; Pichon, C.; Payen, E.; Briois, V.: Intermediate Species Revealed During Sulfidation of Bimetallic Hydrotreating Catalyst: A Multivariate Analysis of Combined Time-Resolved Spectroscopies. *J. Phys. Chem. C* **2017**, *121*, 18544-18556.

(49) Müller, A.; Weinstock, N.; Schmidt, K. H.; Nakamoto, K.; Schläpfer, C. W.: Raman-Spektren Von  $(\text{NH}_4)_2\text{MoO}_4$  Mit  $^{92}\text{Mo}$  Und  $^{100}\text{Mo}$ . *Spectrochim. Acta, Part A: Molecular Spectroscopy* **1972**, *28*, 2289-2293.

(50) Junquera, J.; Cohen, M. H.; Rabe, K. M.: Nanoscale Smoothing and the Analysis of Interfacial Charge and Dipolar Densities. *J. Phys.: Condens. Matter* **2007**, *19*, 213203.

(51) Even, J.; Pedesseau, L.; Kepenekian, M.: Electronic Surface States and Dielectric Self-Energy Profiles in Colloidal Nanoscale Platelets of CdSe. *Phys. Chem. Chem. Phys.* **2014**, *16*, 25182-25190.

(52) Saponi, D.; Kepenekian, M.; Pedesseau, L.; Katan, C.; Even, J.: Quantum Confinement and Dielectric Profiles of Colloidal Nanoplatelets of Halide Inorganic and Hybrid Organic-Inorganic Perovskites. *Nanoscale* **2016**, *8*, 6369-6378.

(53) Shi, N.; Ramprasad, R.: Atomic-Scale Dielectric Permittivity Profiles in Slabs and Multilayers. *Phys. Rev. B* **2006**, *74*, 045318.

(54) Shi, N.; Ramprasad, R.: Dielectric Properties of Ultrathin  $\text{SiO}_2$  Slabs. *Appl. Phys. Lett.* **2005**, *87*, 262102.

## Conflicts of interest

The authors declare no competing interests.

## TOC Graphic

